

压电薄膜传感器建议用粘胶清单

名称	型号	固化条件	厚度	制造商
3M9437 3M9485 3M444 3M9458 3M9703 Scotch 467MP	转移胶带(A 10) 转移胶带(A 25) 双面胶,丙烯酸 双面胶,丙烯酸 Z 轴导电 分层,丙烯酸胶	压力,室温 压力,室温 压力,室温 压力,室温 压力,室温 压力,室温	10 mil 5 mil 4 mil 1 mil 2 mil 2 mil	3M,Adhesives Division 3M Center, Bldg 220-7E-01 St. Pual, MN 55144-1000 (800)362-3550
Densil	硅转移胶	压力,室温	2 mil 5 mil	Flexcon 1 Flexcon Industrial Park Spencer, MA 01562 (508)885-8440 Fax (508)885-8400
Black Max Loctite 495,496	氰基丙烯酸酯胶 (粘稠) 氰基丙烯酸酯胶	室温(10 分钟) 室温	0.001” ~0.003” typical 0.001” ~0.003” typical	Loctite Corp. North American Hdqtrs 1001 Trout Brook Crossing Rocky Hill, T 06067-3910 (860)571-5100
Devcon 5 min	环氧胶(双组分)	室温(5 分钟)	0.001” ~0.003” typical	ITW Devcon 30 Endicott St. Danvers, Ma 01923 (978) 777-1100 Fax (978) 774-0516
RBC 3215 And #AB530 RBC 3200 And #AB532	环氧胶(双组分)	室温或 65 ℃ 时 2 小时	0.001” ~0.003” typical	RBC Industries PO Box 8340 Warwick, RI 02888 401-941-3000 Fax (401) 041-0150
Insulcast 520 Insulgel 70	含底层环氧胶 软环氧胶 (双组分)	底层胶在 60 ℃ 时 2 小时固化 室温或 175 ℉ 时 5 小时	0.001” ~0.010” typical 0.001” ~0.010” typical	Insulcast 565 Eagle Rock Ave. Roseland, NJ 07068 (800) 645-7546 (973) 403-2600 Fax (973) 403-1108
E-Solder 3021	导电环氧胶	室温或加热	0.001” ~0.003” typical	Von Roll Isola USA, Inc. PO Box 1404 New Haven, CT 06505 (203) 562-2171 Fax (203) 562-6864

深圳市爱敏智能科技有限公司

sales@ameaning.com

0755-83277882 18038100666